

3.6V Li/SOCI2 Battery Size: 1/2AA Middle C-Rate Type hi-temperature ER battery



ERI42505-150

# SPECIFICATIONS

(Typical data from the batteries stored at 25+5°C for 12 months)

Nominal Capacity:	0.6Ah
(Capacity measured at 50mA, +25°C/135°C cut-off voltage 2.0V.)	
<b>Open Voltage</b> (at +25°C) :	3.67V
Nominal Voltage(at +25°C, 0.3mA) :	3.60V
Max. Continuous Discharge Current:	100mA

(Current at 50% of nominal capacity is obtained with a cut-off voltage of 2.0V over the range of +25°C to 150°C. For higher currents, consult POWERSTABILITY.)

Pulse Current:	150m

((At +25°C/135°C, an uncharged battery is discharged with a base current of 1mA, and a pulse of 150mA/0.1 second is discharged every 2 minutes during the discharge process, at which time the voltage reading is still above 3.0V. Battery voltage readings will vary depending on pulse characteristics, temperature, and storage conditions. For more severe conditions, please consult POWERSTABILITY for details. Please consult POWERSTABILITY for details)

### Storage (suggest):

+30°C

Α

(Please consult POWERSTABILITY for more demanding or stringent conditions)

### Working Temperate Range:

#### -30°C - +150°C

(Outside the operating temperature range can result in reduced capacity, low voltage readings and low voltage readings at the beginning of the pulse)

# PHYCIAL PROPERTIES

Diameter (max.):	14.5mm
Height (Max.):	25.5mm
Typical Weight:	9g
Lithium Metal Content:	(About)0.17g

### **ADVANTAGES**

Stable high operating voltage and high capacitance

High energy density, high stable current

Wide operating temperature rages (-30°C ~ +150°C)

Low self-discharge rate (annual self-discharge rate is less than 3% at +25°C)

Excellent environmental application characteristics

Stainless steel case (low magnetic resistance to environmental erosion)

### **FEATURES**

A positive structure with proprietary technology

Stainless steel - glass airtight package

Non-combustible electrolyte

High short circuit safety

Comply with GB 8897.4-2008 technical requirements

Meet technical requirements of IEC60086.4:2014

**Warning:** Do not charge, short circuit, heat more than 150°C, decomppose, put into water, directly in the battery shell surface welding, otherwise may cause explosion, combustion and internal acid leakage of the battery.

**POWERSTABILITY SOLUTIONS** 

www.powerstability.com

## ERI42505-150 Size: 1/2AA

Φ4.3 max.

### Size unit :mm


Φ14.5 max.

(GB1804-m if tolerance is not specified) For special connection requests, please consult POWERSTABILITY


### WARNING

- Do not short out the battery
- Do not charge the battery
- Don't pin the batter
- Do not squeeze the battery
- Pay attention to the battery anode and cathode
- Electrical equipment connection is correct
- Do not disassemble the battery
- Do not burn battéries
- Do not mix old and new batteries
- Do not heat the battery to more than 150°C
- Do not directly weld the battery
- Please use a battery with pre-welded pins or wires.


### 1. Typical discharge curve at +135°C (median)



### 2. Voltage graphs at different discharge currents and temperatures (during the stabilisation phase of the discharge)



### 3. Capacity graphs at different temperatures and currents (cut-off voltage of 2.0V)



#### Notice:

POWERSTABILITY reserves the right to change the information coontained in this data sheet without prior notice. Any performance parameters mentioned in this file are for reference only, and the contents of this document can be used as valid contract data only after written confirmation by both parties.

POWERSTABILITY SOLUTIONS www.powerstability.com Email: info@powerstability.com

