

3.6V Li/SOCI2 Battery Size: D Middle C-Rate Type hi-temperature ER battery



ER346155-150

SPECIFICATIONS

(Typical data from the batteries stored at 25+5°C for 12 months)

Nominal Capacity: 13.0Ah

(Capacity measured at 100mA, +25°C/135°C cut-off voltage 2.0V.)

Open Voltage (at +25°C): 3.67V

Nominal Voltage (at +25°C, 0.6mA): 3.60V

Max. Continuous Discharge Current: 800mA

(Current at 50% of nominal capacity at $+25^{\circ}$ C/135°C, 2.0V cut-off voltage, consult POWERSTABILITY for higher currents)

Pulse Current: 1200mA

(At +25°C/135°C, an uncharged battery is discharged at a base current of 50µA, and a pulse of 1200mA/0.1sec is released every 2 minutes during discharge, at which point the voltage reading is still above 2.8V. Battery voltage readings will vary depending on pulse characteristics, temperature, and storage conditions. For more demanding conditions, please contact POWERSTABILITY for details).

Storage (suggest): +30°C

(Please consult POWERSTABILITY for more demanding or stringent conditions)

Working Temperate Range: -55°C - +150°C

(Outside the operating temperature range can result in reduced capacity, low voltage readings and low voltage readings at the beginning of the pulse)

PHYCIAL PROPERTIES

Diameter (max.): 34.2mm

Height (Max.): 61.5mm

Typical Weight: 100g

Lithium Metal Content: (About)3.68g

ADVANTAGES

Stable high operating voltage and high capacitance

High energy density, high stable current

Wide operating temperature rages (-55°C ~ +150°C)

Low self-discharge rate (annual self-discharge rate is less than 3% at +25°C)

Excellent environmental application characteristics

Stainless steel case (low magnetic resistance to environmental erosion)

FEATURES

A positive structure with proprietary technology

Stainless steel - glass airtight package

Non-combustible electrolyte

High short circuit safety

Comply with GB 8897.4-2008 technical requirements

Meet technical requirements of IEC60086.4:2014


Warning: Do not charge, short circuit, heat more than 150°C, decomppose, put into water, directly in the battery shell surface welding, otherwise may cause explosion, combustion arnd internal acid leakage of the battery.

POWERSTABILITY SOLUTIONS

www.powerstability.com

Email: info@powerstability.com

Size: D




Size unit:mm

(GB1804-m if tolerance is not specified) For special connection requests, please consult POWERSTABILITY


WARNING

- Do not short out the battery
- Do not charge the battery
- Don't pin the batter
- Do not squeeze the battery
- Pay attention to the battery anode and cathode
- Electrical equipment connection is correct
- Do not disassemble the battery
- Do not burn battéries
- Do not mix old and new batteries
- Do not heat the battery to more than 150°C
- Do not directly weld the battery
- Please use a battery with pre-welded pins or wires.


1. Typical discharge curve at +135°C (median)



2. Voltage graphs at different discharge currents and temperatures (during the stabilisation phase of the discharge)



3. Capacity graphs at different temperatures and currents (cut-off voltage of 2.0V)



Notice:

POWERSTABILITY reserves the right to change the information coontained in this data sheet without prior notice. Any performance parameters mentioned in this file are for reference only, and the contents of this document can be used as valid contract data only after written confirmation by both parties.



